



HAL
open science

Mechanical properties and microstructure of (emul)gels formed by mixtures of proteins and polysaccharides

Christophe Chassenieux, Taco Nicolai

► **To cite this version:**

Christophe Chassenieux, Taco Nicolai. Mechanical properties and microstructure of (emul)gels formed by mixtures of proteins and polysaccharides. *Current Opinion in Colloid & Interface Science*, 2024, 70, pp.101781. 10.1016/j.cocis.2023.101781 . hal-04482025

HAL Id: hal-04482025

<https://univ-lemans.hal.science/hal-04482025>

Submitted on 28 Feb 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.


L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1 Mechanical properties and microstructure of (emul)gels formed by mixtures 2 of proteins and polysaccharides

3 Christophe Chassenieux* and Taco Nicolai

4 IMMM UMR CNRS6283, Le Mans Université, Avenue O. Messaien, 72085 Le Mans cedex, France.

5 TOC :



6

7 Abstract

8 It is now well established that the combination of proteins and polysaccharides makes it possible to
9 obtain textures that can be used by the food industry. However, consumer demand for more
10 environmentally friendly and healthier foods is leading to the development of new ingredients
11 (particularly plant proteins) for which the know-how acquired on animal proteins cannot be directly
12 transposed. The aim of this review is to take stock of the work published between 2021 and 2023 on
13 gelation of polysaccharide/protein mixtures on their own or in the presence of oil. The emphasis is
14 on structural and rheological studies of these (emul)gels. In addition to the composition and
15 variability of the ingredients, there are a multitude of formulation parameters (pH, salt, temperature,
16 etc.) and shaping parameters (pressure, homogenisation, etc.), which makes it difficult to compare
17 the different studies in order to conclude on general structure/properties relationships.

18

19 Introduction

20 Gels formed by mixtures of proteins and polysaccharides have been studied intensively in the past
21 and continue to raise much interest. One motivation for these studies is to obtain textures that are
22 desirable in food products, but that are difficult to obtain using only proteins. The current tendency
23 to replace animal proteins by plant proteins further stimulates this research since it is often more
24 difficult to obtain desired food textures with the latter. The general features of the interaction
25 between proteins and polysaccharides in aqueous solution as well as those of the formation of gels
26 by these biopolymers are by now well-known and have been extensively reviewed [1-4]. The
27 objective of this review is not to discuss again in detail these general features, but rather to give an
28 overview to the most recent literature in this area and in particular for food grade systems.


29 Therefore, we will only briefly mention the general features here and refer to other reviews for more
30 details.

31 The behavior of aqueous mixtures of proteins and polysaccharides depends on the type of
32 interactions between the two types of biopolymers. If repulsive interactions dominate, segregative
33 phase separation tends to occur with the formation of a phase rich in protein separated from a phase
34 rich in polysaccharides. If attractive interactions dominate, associative phase separation can occur
35 between a phase rich in both types of macromolecules and a dilute aqueous phase. This process is
36 called coacervation if the association is sufficiently weak that the concentrated phase remains liquid.
37 If the association is strong, complexes of proteins and polysaccharides are formed that may form
38 large macroscopic flocs. Association is often driven by opposite charge interactions, though
39 hydrophilic and hydrophobic interactions may also play a role. The net charge of proteins varies from
40 strongly negative at high pH to strongly positive at low pH with a net zero charge at their isoelectric
41 point (pI). Therefore, opposite charge driven association of proteins with anionic polysaccharides
42 such as κ -carrageenan (k-car) occurs at $\text{pH} < \text{pI}$ and with cationic polysaccharides such as chitosan at
43 $\text{pH} > \text{pI}$. However, this association can happen even when the proteins and polysaccharides have the
44 same net charge close to the pI where the proteins have both negative and positive patches. We
45 note that when the proteins and polysaccharides form complexes, segregative phase separation can
46 sometimes still occur between the complexes and polysaccharides or proteins if the latter are
47 present in excess. Liquid-liquid phase separation leads to the formation of domains of the minority
48 phase suspended in the continuous majority phase that grow leading eventually to macroscopic
49 phase separation. The rate at which this process occurs depends on the strength of the interactions,
50 but also on the viscosity of the phases. Phase separation leads to loss of the mixing entropy and is
51 therefore more likely to occur if the molar mass of the components is higher.

52 Gelation involves the formation of crosslinks between the macromolecules leading to the formation
53 of a system spanning network that needs to be sufficiently strong to resist gravity. In mixtures the
54 network can be formed by crosslinks between the proteins, between the polysaccharides or both
55 [5]. It is also possible that the proteins bind to the polysaccharides. Gelation can be induced by
56 various methods [6]. Gelation of globular proteins is induced by denaturation exposing hydrophobic
57 groups leading to the formation of crosslinks between denatured proteins [7]. Denaturation is most
58 often induced by heating (leading to so-called heat-set gels), but can also be achieved by applying
59 high pressure. Other gelation methods can be applied at low temperatures (cold-set gels) and involve
60 adjusting the pH closer to the pI or adding salt, both of which reduce electrostatic repulsion. Using
61 these methods most crosslinks are physical though disulfide bridging can also occur. Covalently cross-
62 linked protein gels can be formed by adding enzymes such as transglutaminase. Gelation of
63 polysaccharides often involves addition of salt combined with cooling, but in a few cases it is induced
64 by heating [8]. The gelation rate and the microstructure of pure protein and polysaccharide gels
65 depends on the type of protein and polysaccharide, but also on the environmental conditions such as
66 temperature, type and concentration of salt, pH and polymer concentration.

67 In mixtures, gelation of proteins and/or polysaccharides will be influenced by the interaction
68 between the two macromolecules leading to gels with different microstructures, see figure 1. If the
69 interaction between the proteins and the polysaccharides is weak, both components are
70 homogeneously mixed with either one or both components crosslinking with itself. If the interaction
71 between the two components is strong the gelation rate is very important, because phase separation
72 occurs during the crosslinking process. If crosslinking is slow compared to phase separation, the
73 latter can become macroscopic before the network fills the whole space. If phase separation is
74 sufficiently slow it can be arrested on a microscopic scale by crosslinking one or both components

75 into a space filling network. In the case of segregative phase separation the network will then contain
 76 domains of the other phase that can still be liquid. The size and volume fraction of the inclusion
 77 domains depends on the composition and the relative kinetics of crosslinking and phase separation,
 78 which in turn depend on the type of proteins and polysaccharides, their composition in the mixture
 79 and the environmental conditions. In the case of associative phase separation, the network will
 80 contain domains with low concentrations of either component. It is obvious that gels with a wide
 81 range of properties can be obtained with mixtures if we consider that the properties of pure protein
 82 and polysaccharide gels already depends on their type, concentration and environmental conditions.
 83 These properties will furthermore be influenced by the presence of other ingredients such as oil or
 84 sugar.



85
 86 Figure 1 Schematic drawing of different types of mixed protein/polysaccharide gels: unbound
 87 polysaccharide homogeneously distributed throughout the protein network (A) or vice versa (B);
 88 segregative (C) or associative (D) microphase separated gel.

89 Even if we consider only food applications, there are dozens of different protein and polysaccharides
 90 types one can choose from, which means that the number of different binary mixtures is enormous.
 91 In fact, most often the protein component is itself a mixture of different types that can interact with
 92 each other in ways that depend on the environmental conditions. Currently, it is not possible to
 93 predict the properties of a mixed gel at a particular environmental condition from its composition
 94 even if the properties of the individual components are known. Therefore, each mixture of interest
 95 needs to be investigated separately. Full understanding of a particular mixture requires elucidating
 96 the effects of varying the concentration, the composition, the pH, the ionic strength, the processing
 97 conditions such as the heating temperature and duration, and other parameters of potential interest.
 98 No single study can provide such a full understanding. For a few systems several studies focussing on
 99 different conditions have been published, but even that has not resulted in full understanding of
 100 their properties at all conditions. For most mixtures that have been investigated current knowledge is
 101 patchy with results obtained only at particular concentrations, compositions and environmental
 102 conditions. An additional complication is that, as was mentioned above, the protein component is
 103 often itself a mixture that can vary in composition. This is in particular a problem for plant proteins
 104 for which the composition and also the state (native vs aggregated) of the proteins strongly depends
 105 on the extraction method. With such systems it is difficult even to compare studies of nominally the
 106 same mixtures reported by different research groups. A similar difficulty arises for nominally the

107 same polysaccharide, which can vary not only in the molar mass distribution, but also in
108 configuration such as the degree of acetylation or methylation.

109 Given the huge range of systems that can be investigated, the choice to study a particular system has
110 to be motivated by its potential for application, which includes considerations of cost, nutritional
111 value and environmental sustainability. The aim can be to investigate the potential of a particular
112 type of polysaccharide or protein, e.g. because it is produced in particular areas, is claimed to have
113 health benefits, or can potentially valorise waste products. The aim can also be to produce gels with
114 certain dynamic mechanical properties that give a desired texture to a particular industrial food
115 product. Another issue, which has attracted much attention in recent years, is the possibility to
116 incorporate functional ingredients, such as flavors and antioxidants, that require protection and
117 controlled release at desired locations, e.g. in the mouth or rather in the intestines. As was
118 mentioned above, the properties of any chosen mixture will depend on the pH, the salt
119 concentration and the processing method. This can be an advantage in that the conditions can be
120 varied in order to optimize the desired properties, but it can also be a constraint if particular
121 conditions are required e.g. for reasons of taste or industrial production methods.

122 Here we review the literature on gels formed by protein/polysaccharide mixtures published between
123 2021 and early 2023 focussing on food related systems. A range of different techniques have been
124 used to study different aspects of the gels, but in this review only the mechanical properties and the
125 microstructure of the gels will be considered. The stiffness of the gels can be characterized by the
126 storage shear modulus (G') determined in the linear response regime. Another mechanical property
127 that is often determined is the hardness, also called gel strength, defined as the maximum force
128 during compression, which may, however, depend on the geometry that is used and the rate of
129 compression. Confocal laser scanning microscopy (CLSM) is a non-invasive method to determine the
130 microstructure of the gels with a resolution of approximately 0.1 μm . Scanning electron microscopy
131 (SEM) has a higher resolution, but requires severe treatment that often perturbs the gel structure as
132 was nicely illustrated recently by Zhang et al. [9] who showed both CLSM and SEM images of the
133 same gels at different scales. SEM images showed large structures at low resolution for gels that
134 CLSM showed were perfectly homogeneous on these length scales, see Fig. 1. Li et al. 2022 also
135 noticed the difference between the microstructure of casein gels as observed by SEM and CLSM. The
136 microstructure of the gels influences its mechanical properties, but there is no straightforward
137 relationship between the two, because the latter are determined by the flexibility of the structure
138 and resistance of the crosslinks to stress that cannot be seen in a static image of the structure.
139 Nevertheless, investigation of the microstructure is important, because it determines the visual
140 aspect of the gels and to a large extent their water and/or oil retention capacity.

141 **1. Gels**

142 Gels of protein/polysaccharide mixtures can form by crosslinking the proteins, the polysaccharides or
143 both. The effect of mixing on the properties can be gauged by comparing with the equivalent pure
144 protein and polysaccharide systems. Globular proteins in aqueous solution tend to aggregate when
145 denatured by heating and form a gel if the concentration is sufficiently high. These gels persist and
146 are usually even stiffer after cooling. Globular protein gels can also be formed at room temperature if
147 the globular proteins are aggregated by preheating and the electrostatic repulsions are subsequently
148 reduced by reducing the pH or adding salt. Two types of non-globular proteins, gelatin and casein
149 that are often present in food products, can also form gels without heating. Gelatin solutions are
150 liquid above 30°C and gel reversibly below 25°C. Casein solutions gel when the pH is reduced in-situ
151 to close to its $pI \approx 4.5$. In-situ acidification is usually done by adding glucono delta lactone (GDL)
152 which degrades slowly in time releasing protons. Gelation of certain polysaccharides such as gellan,

153 k-car, alginate and pectin can be induced by cooling, acidification and/or adding adding salt [5, 8, 10].
154 Others such as guar and xanthan form increasingly viscous solutions with increasing concentration
155 that may appear as gels at higher concentrations. In following, we will first review investigations of
156 the effect of adding polysaccharides on the properties of protein gels formed at high and low
157 temperatures and then the effect of adding protein on the properties of polysaccharide gels. The
158 review of purely aqueous systems will be followed by an overview of the use of
159 protein/polysaccharide mixtures on the stability of oil in water emulsions and the properties of
160 emulsion gels.

161

162 *1.1 The effect of polysaccharides on heat-set protein gels*

163 In almost all studies covered by this review a fixed heating protocol was used consisting of heating up
164 to a relatively high temperature varying between 80°C and 95°C, holding the temperature between
165 10 and 50 min followed by cooling. Generally, it is not explained why a particular heating protocol
166 was chosen and it is likely the mechanical properties of the gels will depend to some extent on the
167 heating protocol that was chosen as was shown by Zhang et al. [9]. Serabi et al. [11] studied the
168 influence of adding basil seed gum (BSG) on gels formed by heating whey protein isolate (WPI)
169 solutions at pH 7 and 0.05 M NaCl. WPI contains a mixture of globular proteins, mostly β -
170 lactoglobulin (b-Ig) and α -lactalbumin. Segregative phase separation was observed in mixtures
171 before heating at higher BSG concentrations. For a given heating rate, gelation occurred at a lower
172 temperature if more BSG was present and stiffer gels were formed. In mixtures of b-Ig and the
173 polysaccharide Levan at pH 7 segregative phase separation was found that was favored by increasing
174 the molar mass of the polysaccharide or by adding 0.1 M NaCl [12]. During a heating ramp, b-Ig
175 solutions gelled at a lower temperature when salt was added, because the aggregation rate is faster
176 when electrostatic repulsion is screened. The apparent gelation temperature depends, of course, on
177 the heating ramp rate, but at a given rate it decreased with increasing Levan concentration and more
178 so when its molar mass was higher. G' measured after keeping the samples 20 min at 90°C was much
179 larger in the presence of salt, in part due to the faster gelation rate and in part due to the different
180 structure of the gels. Addition of Levan led to an increase of G' up to a certain concentration, but G'
181 decreased again when more Levan was added. It was suggested that segregative phase separation
182 induced by adding either Levan or BSG increased the gel stiffness by locally increasing the protein
183 concentration, but strong phase separation at higher Levan concentrations weakened the gel
184 perhaps by reducing the connectivity between protein rich domains.

185 In another study *Lycium barbarum* polysaccharides (LBP) were added to WPI [13]. Also in this study
186 the WPI concentration was fixed at 12%, but the effect of 3 different polysaccharide concentrations
187 at 3 pH values was investigated. WPI gels were formed by heating. Addition of 0.1 % LBP increased
188 G' , but 0.5 % had less effect and adding 1% decreased G' with respect to pure WPI gels. The values of
189 G' and the quantitative effect of LBP depended on the pH with stiffer gels being formed at pH 5.2,
190 close to the pI of WPI, than at pH 3 and pH 7. Babaei et al [14] studied the effect of adding alginate or
191 k-car with or without CaCl_2 on gels formed by heating WPI solutions. The system was studied at one
192 particular pH (6.7) and WPI concentration (12 %) with and without 0.25 % polysaccharide and with
193 and without CaCl_2 (30 mM). Addition of either polysaccharide increased the gel hardness and the
194 addition of CaCl_2 increased it further. It is not clear from this study and the one by He et al. [13]
195 whether the interactions between the polysaccharides and the whey proteins were attractive or
196 repulsive.

197 Jiang et al. [15] studied WPI (10 wt%) mixed with 2 wt% *mesona chinensis* polysaccharide (MCP) at
198 different pH. After heating, a stable self-supporting gel was formed at pH 10, but not at lower pH
199 down to pH 4 implying that MCP inhibits gelation of WPI at lower pH. These authors did not compare
200 the mixed systems with equivalent pure WPI so that the effect of adding MCP cannot be judged. The
201 same research group investigated the effect of adding CaCl₂ to this mixture at pH 10 [16]. They found
202 that adding CaCl₂ reduced the stiffness and the hardness of the gels, whereas CLSM showed that the
203 microstructure became more heterogeneous. Guo et al. [17] observed that G' and the hardness of
204 gels formed by a mixture of gellan and WPI varied with the pH. However, no comparison was made
205 with the equivalent pure WPI gels.

206 Turning to globular plant proteins, Johansson et al. [18] found that replacing a small fraction of faba
207 bean proteins by either polysaccharide fibres or by starch led to an increase of G' of gels formed by
208 heating. The gels containing more fibres of starch were more heterogeneous with microdomains rich
209 in fibre or starch, which could explain that they had a lower fracture stress and strain. Addition of
210 konjak glucomannan (KGM) significantly increased G' of SPI (10%) gels formed by heating [19] and
211 CLSM image showed segregative microphase separation between the two components. Adding low
212 methoxy pectin to pea protein isolate (15%) gels formed at pH 6.5 by heating led to an increase of G'
213 with increasing pectin concentration and the gel was more heterogeneous [20]. Large protein
214 aggregates were formed in solutions with pectin suggesting complexation between the two
215 components.

216 Jiang et al. [21] and Lu et al. [22] studied the influence of adding k-car on gels formed by heating
217 solutions of oyster protein isolate (OPI) and SPI, respectively. The elastic modulus and the hardness
218 of the gels increased strongly with increasing k-car concentration. Lu et al. [22] showed that G' of the
219 mixed gels decreased sharply upon heating and increased again upon cooling, which is caused by the
220 reversible gelation of k-car. It is clear, therefore, that for these mixtures the mechanical properties of
221 the mixed gels were increasingly dominated by the gelation of k-car during cooling. Unfortunately, no
222 results for equivalent pure k-car gels were reported, which would allow one to determine the effect
223 of the protein on the k-car gel. The stiffness of k-car depends not only on its concentration, but also
224 on the type and concentration of ions that are present [23], information about which should
225 therefore be provided. CLSM images showed that the SPI/k-car mixed gels were heterogeneous. It
226 was suggested that complexation occurred in spite of the fact that both components were negatively
227 charged at pH 7 at which the measurements were done, but at higher k-car concentrations also
228 segregative micro phase separation was thought to occur. Lei et al. [24] compared the effect of
229 adding k-car or guar gum on gels formed at pH 8 by heating solutions of phyco cyanate (16% w/v), a
230 protein extracted from *Spirula*. G' of the gels measured at 25°C increased with the addition of more
231 k-car up to the maximum added (0.4%). With guar G' increased at 0.1%, but decreased when larger
232 amounts were added. The effect was stronger for k-car, perhaps because it gelled in the mixtures,
233 but it is difficult to conclude since no comparison with pure polysaccharide solutions was made.
234 CLSM images showed that the pure protein gels had a heterogeneous microstructure which
235 appeared less heterogeneous in the presence of 0.4 % k-car and more heterogeneous with 0.4 %
236 guar.

237 An investigation of the effect of adding 0.5 % w/v dextran or dextran sulfate (DS) on gels formed by
238 heating egg white protein at pH 4, 7 and 9 showed little effect of dextran on G', but in the presence
239 of DS a significant decrease at pH 4 and an increase at pH 7 [9, 25]. The hardness defined as the
240 maximum force during compression was much smaller both in the presence of dextran and DS at pH
241 4, and somewhat larger in the presence of DS at pH 7. In this study the authors varied the holding
242 time at 90°C and showed that the hardness increased significantly with increasing holding time. The

243 negative effect at pH 4 was attributed to extensive complex formation at this pH and the positive
244 effect at pH 7 to weak attractive electrostatic attraction [26]. CLSM images showed that the addition
245 of DS led to more homogeneous gels, which explains why these gels were less turbid.

246 Zhuang et al. [27] and Zhang et al. [28] studied the effect of adding KGM on gels formed by heating
247 myofibrillar protein (MP) solutions at pH 7. The mixtures contained a high concentration of salt (0.6
248 M). Zhuang et al reported for MP at 4% that adding KGM improved the hardness up to 1%, but
249 decreased at higher concentrations, whereas Zhang et al found that both G' and the hardness
250 increased up to the highest concentration tested of 2%. CLSM images showed segregative
251 microphase separation between the components. Zhang et al. [28] quantified the synergistic effect
252 of KGM on MP gelation by comparing the evolution during heating of the shear moduli of the mixture
253 with that of the sum of the individual components. They also quantified the microstructure of the
254 gels in terms of a fractal dimension derived both from the rheology and from CLSM images. However,
255 different values were obtained from the different techniques and their physical meaning is not clear
256 for these microphase separated systems.

257 The effect of adding either guar gum, locust bean gum or xanthan on heat induced gelation of quinoa
258 protein isolate was studied at pH 7 in the presence of 50 mM NaCl [29]. CLSM showed that addition
259 of polysaccharide led to formation of larger protein aggregates and after heating to a more
260 heterogeneous gel. However, since the polysaccharides were not labelled it is not clear the CLSM
261 images whether associative or segregative microphase separation had occurred. G' and the yield
262 stress of the heat set gels increased with increasing polysaccharide concentration up the highest
263 tested (0.2%). The effect depended on the type of polysaccharide being smallest for guar gum and
264 largest for xanthan.

265 Almost all investigations discussed so far showed an increase of the stiffness when more
266 polysaccharide was added up to a certain amount, but in some cases larger quantities of
267 polysaccharide caused a decrease of G' . Quantitatively, the effects depend on the particular mixture
268 and the conditions at which the gels were produced. In none of these studies the equivalent pure
269 polysaccharide solution was studied, which means that it is difficult to tell whether in some cases the
270 improvement was not simply caused by gelation of the polysaccharide. This is particularly obvious in
271 the study by Jiang et al. [21] who added k-car, which can form a strong gel by itself. In cases where
272 both proteins and polysaccharides form a crosslinked network one should consider the influence of
273 proteins on the polysaccharide network as well as the influence of the polysaccharides on the protein
274 network.

275

276 *1.2 The effect of polysaccharides on cold-set protein gels*

277 As was already mentioned, globular protein solutions can also form gels at low temperatures if they
278 are denatured and aggregated by preheating and subsequently the electrostatic repulsion is reduced
279 by acidification or adding salt. Brito et al. [30] gelled preheated SPI solutions (15 wt%) at 10°C by
280 adding CaCl_2 . Addition of small quantities of xanthan (0.1%) or locust bean gum (0.2%) led to stiffer
281 gels with a lower creep compliance. Bu et al. [31] preheated a mixture of tenebrio molito protein and
282 low methoxy (LM) pectin at pH 3.4 where the two components formed complexes. They
283 subsequently induced gelation by adding CaCl_2 and G' was found to increase with increasing Ca^{2+}
284 concentration. Solutions of LM pectin gel by themselves in the presence Ca^{2+} and the preheated
285 denatured proteins could perhaps also form a gel by themselves in the presence of Ca^{2+} . Therefore,
286 equivalent pure protein and polysaccharide solutions need to be investigated before one can draw
287 conclusions about the effect of complexation on the gels. Adding pectin to preheated pea protein

288 aggregates was found to induce microphase separation [20]. A gel containing elongated pectin rich
289 microdomains could be formed by enzymatically crosslinking the proteins while applying a shear.


290 An alternative method to obtain proteins gels at low temperatures is to use gelatin or casein
291 proteins. The stiffness of a gelatin gel increases with time at a rate that increases with decreasing
292 temperature. Ji et al. [32] added hydroxy propyl methylcellulose (HPMC) to gelatin in an attempt to
293 increase the melting temperature. HPMC has the particularity to form a gel above about 55°C. It was
294 found that gelatin and HPMC phase separate, but the mixtures gel at 25°C when the gelatin rich
295 phase is continuous. The gelatin rich phase contained an unknown amount HPMC, which led to a
296 small increase of the melting temperature by 3°C, but significantly reduced G'. The microstructure of
297 the mixed gel varied with the HPMC content, but there was no clear relationship between the
298 microstructure and G'. Interestingly, the viscosity measured at the same temperature after a heating
299 and cooling ramp was different showing that for such a phase separating system the history of the
300 sample is important.

301 Addition of a small quantity of hsian-tsoo gum (HG) to gelatin solutions slowed down the gelation
302 rate at 22°C, but at larger quantities it increased the gelation rate [33]. The presence of HG did not
303 influence G' much. The yield stress upon compression increased a little with small amounts of HG,
304 but decreased when a larger amount was added. CLSM showed a heterogeneous structure for the
305 mixed gels, but there was no clear relationship between the microstructure and the mechanical
306 properties. The authors concluded that HG formed complexes with gelatine by association of
307 opposite charges, but that also microphase separation occurred between gelatin and HG rich phases.
308 To complicate matters further, heating to 80°C influenced the properties at 22°C. Zhang et al. [34]
309 added polysaccharides extracted from mulberry leaves to gelatin. They observed that complexes
310 were formed, in particular at higher pH even though both components were negatively charged.
311 Adding mulberry polysaccharides reduced the shear dependent viscosity and the elastic modulus
312 measured at 25°C, in a manner that depended not only on the pH, the ionic strength and the quantity
313 of added polysaccharide, but also on the manner in which the polysaccharides were extracted.

314 The polysaccharides used in these 3 studies did not gel by themselves at lower temperatures
315 contrary to mixtures with k-car studied by Makarova et al.[35]. Much stiffer, but also more fragile
316 gels were formed in the presence of k-car. SAXS measurements showed that different structural
317 heterogeneities were present in the gels with and without k-car. Most likely the properties of the k-
318 car dominated the properties of the mixed gel, but no results were reported for the equivalent pure
319 k-car gels so that the effect of the proteins on the k-car gel remains unknown.

320 Another type of protein that gels at room temperature is casein, which is the main protein
321 component of milk and is present in milk as colloidal particles called casein micelles. Aqueous
322 solutions of casein gel after reducing in-situ the pH towards the pI of the proteins. Li et al. [36-38]
323 studied the influence of adding the anionic polysaccharides ALG, gellan or the neutral polysaccharide
324 methyl cellulose on the properties of casein gels at 8% formed after adding GDL. The hardness of the
325 gel increased with increasing ALG or MC concentration up to a maximum at 0.4% decreasing at
326 higher concentrations. In the presence of gellan the hardness increased progressively up to the
327 highest concentration tested (0.6%). Gelation was faster when more polysaccharide was present,
328 which in the case of ALG was shown to be caused by a faster decrease of the pH and CSLM images of
329 the gels showed an increasingly heterogeneous microstructure with protein poor domains
330 surrounded by protein rich domains, see fig. 2. At low concentrations casein was shown to form
331 complexes with ALG, which inhibited large scale flocculation of the caseins below pH 5.5 and similar
332 complexation is also expected with the gellan. The authors suggested that segregative phase
333 separation occurred at high pH followed by complexation of the anionic polysaccharides with the

334 proteins at lower pH. However, since the polysaccharides were not labeled it was not possible to
 335 observe their distribution in the gels as a function of the pH. It is remarkable that the three types of
 336 polysaccharide had a similar effect on the casein gels even though the anionic polysaccharides
 337 formed complexes with the proteins, whereas the neutral MC is not expected to do so.



338
 339 Fig. 2 Evolution of the storage and loss moduli during acidification of casein solutions with different
 340 amount of ALG added. CLSM images taken at different time during acidification are also shown.
 341 (reproduced with modifications from [9]).

342 It appears that cold-set gels formed by globular protein aggregates or casein also become stiffer
 343 when polysaccharides are added in modest quantities. However, gelatin gels appear to become less
 344 stiff, at least when the polysaccharide itself does not form a strong gel as was the case in mixtures
 345 with k-car studied by Makarova et al. [35]. It seems that the added polysaccharides interfere with the
 346 crosslinking of gelatin.

347

348 1.3 The effect of proteins on polysaccharide gels

349 If the proteins don't crosslink, gels can still be formed by physical crosslinking of the polysaccharides
 350 in the mixtures. Hu et al. [39] investigated gelation of k-car in the presence of native b-lg or in the
 351 presence of b-lg aggregates in the form of nanoparticles or fibrils formed by preheating at pH 5.8 and
 352 pH 2, respectively. The effect of the proteins was investigated at pH 9 where both components are
 353 negatively charged and at pH 4 where the proteins have a net positive charge and form a complex
 354 with the still anionic k-car. At pH 9 gelation of k-car during cooling was little influenced by the
 355 presence of the proteins, but at pH 4 the proteins perturbed the coil-helix transition of k-car and as a
 356 consequence G' decreased strongly with increasing protein concentrations. This effect was stronger
 357 when b-lg was added in the form of fibrillar aggregates suggesting a more extensive interaction of
 358 the k-car chains with the latter. A reduction of G' caused by complexation of native b-lg was also
 359 observed by Taheri et al [40] for the anionic polysaccharide cress seed mucilage at pH 3.5. Lin et al.
 360 [41] heated mixtures of peanut proteins with k-car or gellan at 90°C under stirring. Gels were
 361 subsequently formed by cooling to room temperature. These gels melted again upon heating to 80°C.
 362 As might be expected, G' and the hardness of the gels increased with increasing polysaccharide

363 concentration, but no comparison was made with equivalent pure polysaccharide gels so that it is
364 not possible from this study to judge the effect of the proteins on the polysaccharide gelation. The
365 reversible gelation was exploited to use these mixtures for 3D-printing.

366 Kazemi et al. [42] studied the effect of adding WPI on gelation of gellan solutions induced by adding
367 FeSO_4 . The measurements were done at pH 7 where both components are negatively charged and
368 not expected to form complexes. As might be expected G' was larger when the fraction of gellan was
369 larger at a given total polymer concentration. Here also, no comparison was made with pure gellan
370 gels

371 The influence of adding native amarynth protein isolate (API) or bean protein isolate (BPI) on xanthan
372 gels was studied by Cortez et al. [43]. Whereas pure xanthan gels were formed at pH 8 and 9, in the
373 presence of API, gels were formed between pH 7 and 9 and in the presence of BPI close to pH 7. The
374 proteins by themselves did not form a gel. The effect was attributed to association between the two
375 types of biopolymers. In a follow up study the authors found that if the pH was decreased in-situ
376 using GDL, API/xanthan gels were also formed at pH 4 and pH 5.5 [44]. Most likely, the network is
377 broken if the pH is decreased by adding a strong acid under stirring and a suspension of aggregates is
378 formed. The hardness of the gels was found to be much larger below the pI of the protein at pH 4
379 then above the pI at pH 5.5. This was attributed to strong electrostatic attractive interaction at pH 4,
380 whereas hydrophobic interactions were thought to be more important at pH 5.5 For a given total
381 biopolymer concentration of 1%, the hardness of the gels was found to decrease with increasing API
382 and decreasing xanthan content at pH 4. Similar results were obtained for mixtures of BPI and
383 xanthan below (pH 4) and above (pH 4.5) pI, but the effect of the pH on the hardness and G' was
384 much smaller [45]. At pH 4.5 there was a significant decrease of the hardness with increasing protein
385 content. Unfortunately, no comparison was made with pure xanthan gels.

386 Methyl cellulose solutions gel during heating above approximately 50°C and the gels melt during
387 cooling below about 40 °C. Soy globulins were found to form complexes with methylcellulose already
388 at room temperature, which led to a decrease of G' of the gel formed at 70°C with increasing protein
389 up to 0.4% [46]. At higher protein concentrations tested up to 1.6%, G' increased again, but did not
390 reach the value of pure MC.

391 Protein hydrolysates derived from scallop were found to form complexes with the polysaccharides in
392 mixtures of xanthan and k-car at a weight ratio 3:2 [47]. Gels were formed at total biopolymer
393 concentration of 1.5% with G' increasing with increasing polysaccharide content. For a given mixture,
394 G' increased with decreasing pH between pH 9 and pH 3, which could perhaps be related to stronger
395 electrostatic attractive interaction between the proteins and the anionic polysaccharides. No
396 comparison was made with gels of just the polysaccharide mixture at the same conditions.

397 Finally, Yao et al. [48] added gelatin to a solution of *Artemisia sphaerocephala* Krasch polysaccharide
398 (ASKP). By itself ASKP slowly formed a gel when FeSO_4 was added at pH 4, but the gelatin by itself did
399 not gel at the conditions studied. Addition of gelatin slowed down gelation of the polysaccharides at
400 25°C and reduced both G' and the hardness measured after 3 days. The influence of gelatin on the
401 polysaccharide gelation was attributed to complexation caused by opposite charge interactions,
402 which implies that it will strongly depend on the pH.

403 The main conclusion that can be drawn from these studies is that if the added proteins form
404 complexes with the polysaccharides they interfere with gelation of the latter leading to gels that are
405 less stiff. Quantitatively, the effect will be different for each type of polysaccharide and it depends on
406 the type and morphology of the proteins as well as the pH. Most likely, it will also depend on the
407 ionic strength, which was not considered in these studies.

408 2. Emulgels

409 Proteins, either individually or in the form of aggregates, can also be combined with polysaccharides
410 to effectively stabilise water/oil interfaces. The first objective is to improve the stability of emulsions
411 over time or as a function of external parameters (pH, temperature, freeze-drying, etc.) compared
412 with the performance of emulsions prepared with the two ingredients considered separately. This
413 involves combining i) the rapid adsorption kinetics of individual proteins at these interfaces or ii) the
414 Pickering stability provided by their aggregates and iii) the (electro)steric stabilisation provided by
415 the polysaccharides [49]. Here again, numerous protein/polysaccharide combinations have been
416 explored in the recent literature, not to mention variations in pH, temperature, concentration,
417 composition, nature of the oil or processing conditions of the formulations considered. Therefore, it
418 is quite difficult to rationalise the results as a whole, because the performance of each new type of
419 stabiliser is not always evaluated in the same way, which makes it impossible to obtain a proper
420 comparison. Another option is to produce emulgels, i.e. gelled emulsions that can be considered as
421 soft solids whose textural, nutritional and sensory properties can be optimised to lead to cheese [50]
422 or meat analogues [51] or as fat replacers. In both cases, in response to the concerns of vegan
423 consumers, ingredients derived from plants for both oils and proteins provide interesting alternative.
424 New functions can also be envisaged for these emulsions, such as better resistance to oxidation of
425 the oil phase thanks to thicker interfaces acting as a physical barrier [52-54] or the possibility of using
426 them as “inks” for 3D printing of foods, which requires specific rheological profiles [55]. Before
427 discussing the recent literature on the use of protein/polysaccharide complexes to obtain stable
428 emulsions and emulgels, we will consider briefly the influence of their preparation method on their
429 properties.

430 2.1 Influence of the preparation method of the emulsions

431 Emulsions involving protein/polysaccharide complexes can in fact be obtained in two different ways.
432 The first, known as *in situ*, involves preparing a primary emulsion stabilised by proteins and then
433 adding the polysaccharide which will adsorb onto the primary droplets. It has been illustrated for
434 instance by Shi et al. [56] who have studied fish oil emulsions stabilised with caseinates, to which
435 sulphated fucan was added. Emulsions formulated in this way are stable if sufficient polymer is
436 added to saturate the interfaces and prevent the formation of bridges between oil droplets. The salt
437 and pH stability of the resulting emulsions is superior to that of primary emulsions, particularly for
438 high molar mass polymers, which is attributed to a thicker interface. The latter limits the flocculation
439 of oil droplets which increases the specific surface area of the oil phase resulting in increased
440 digestion rate. The increase in stability as a function of pH of complex-stabilised emulsions has also
441 been reported by Juyang et al. [57] for sodium caseinate/pectin mixtures.

442 The second way for obtaining emulsions stabilised by protein/polysaccharide complexes involves
443 preparing protein/polysaccharide complexes *ex situ* and dispersing them in the aqueous phase,
444 which is then emulsified with oil. The *ex situ* method makes it possible to better study and optimise
445 the characteristics of the complexes before they are used as stabilisers, although their interaction
446 with the interface and their further processing may ultimately affect these characteristics. Liu et al.
447 [58] compared the two processes using hemp protein isolates (HPI) with various polysaccharides. The
448 emulsions prepared *in situ* proved to be more stable over time than those prepared *ex situ*, but less
449 so with temperature or salt addition, which was attributed to differences in the interface structures.
450 However, the exact composition of this interface and its degree of stratification as a function of the
451 production process of the emulsion have not been reported. Using sodium caseinate/pectin
452 mixtures, Liao et al. [59] also concluded that emulsions prepared *in situ* were more stable, while
453 specifying the electrostatic nature of the pectin/caseinate interaction mechanism as evidenced from

454 ITC measurements. However, these authors stressed the need to control the order and speed of
455 addition of the components: the primary emulsion should be added to the pectin rather than vice
456 versa, in order to limit flocculation of the oil droplets by bridging.

457 *2.2 From emulsions to emulgels*

458 Emulgels can be obtained by gelation of the continuous phase in the same manner as in the pure
459 aqueous systems discussed above. Lin et al. [60] formed emulgels from mixtures of SPI and alginate
460 by calcium ions that cause crosslinking of alginate. Here again, the order of addition has a
461 considerable influence on the microstructure of the emulgels due to the presence of flocculated oil
462 droplets when the polysaccharide is added to the primary emulsions. The gelling kinetics are also
463 slower and the final modulus of the emulgel lower in the latter case due to the entrapment of some
464 alginate chains between the flocculated droplets. When alginates were combined with casein
465 micelles instead, the results were very different. Despite the lack of affinity between the two
466 partners, their mixtures with oil can also give rise to emulgels after acidification as was reported by Li
467 et al. [61] In this peculiar case the order of addition is of less importance, casein micelles rather than
468 alginate stabilize oil/water interface inducing the location of oil droplets mainly in the casein phase.
469 Upon acidification, the casein phase displays gelation and eventually when the pH is low enough, the
470 interaction between alginate and casein becomes attractive. The structure of these emulgels is
471 controlled by the casein/alginate ratio rather than by the way the mixtures proceeded.

472 In the previous example, gelation of the continuous phase is induced by the addition of calcium ions
473 or protons. However, it can also occur without using any external crosslinking agents as described
474 hereafter. Sun et al. [62] prepared emulgels using fibrillar aggregates of WPI (WPIF) complexed with
475 arabic gum that were insoluble between pH 4.6 and 6. For an oil volume fraction of 60%, stable
476 emulsions were obtained either as liquids with WPI/AG complexes or as emulgels with WPIF/AG
477 complexes, which was explained by the fibrils' greater propensity to complex AG. The result was the
478 formation of bundles, which promoted the formation of a network within the emulsion. In terms of
479 sensory analysis, these emulgels are on a par with commercial mayonnaises. Similarly, Dong et al.
480 [63] produced emulgels by complexing ovotransferrin fibrils and pectins with a pearl necklace
481 structure. With the complexes, the moduli of emulgels formed by mixing with canola oil and
482 candelilla wax were increased by more than one order of magnitude compared with their
483 counterparts stabilised by fibrils alone. However, an anisotropic shape of the complexes is not a
484 prerequisite for achieving emulgels as evidenced by Su et al. [64]. They produced complexes based
485 on beta-lactoglobulin microgels and PGA whose hydrophilicity increased with the proportion of PGA
486 and which were used to stabilise triglyceride emulsions. PGA stiffened WPI microgels, which
487 improved the emulsion stability and led to the formation of emulgels when the oil volume fraction
488 was increased. Some emulgels resisted centrifugation and their microstructure, measured by
489 confocal microscopy, indicating the presence of a PGA network in the continuous phase.

490 Formation of emulgels may circumvent the poor efficiency of plant derived proteins to stabilize
491 emulsions. This has been exemplified for SPI and various polysaccharides (pectin, kappa and iota
492 carrageenan) by Ge et al [65] who heated soy bean oil emulsions above the denaturation
493 temperature of SPI at pH4. At these conditions, electrostatic interactions take place between the
494 polysaccharides (to a bigger extent with k-car) and the denatured SPI and the anchoring of the latter
495 at the oil interface resulting in the formation of emulgels with tunable rheological properties
496 depending on the polysaccharide.

497 In conclusion, protein and polysaccharide complexes can form a new type of stabilisers of emulsions
498 that is much more effective than their individual components. However, the number of combinations

499 is enormous given that other parameters such as composition, temperature, etc. can also be
500 modified to a large extent. When starting from a protein-stabilised primary emulsion, the
501 polysaccharide phase must be added in a controlled manner to avoid flocculation of the oil droplets.
502 Emulgels can be derived from these emulsions by cross-linking the continuous phase, which can
503 overcome certain disadvantages presented in particular by some vegetable protein isolates which are
504 unable to stabilise emulsions over time. Emulgels can also be formed starting from emulsion
505 stabilised by a mixture of proteins and polysaccharide displaying segregative properties. These
506 emulgels meet the requirements in terms of rheological profiles for 3D printing of food that requires
507 easy flow during extrusion followed by fast setting after extrusion. Here we have focused our review
508 on emulsions based on oil but should be noted that recent literature also reports the use of
509 protein/polysaccharide complexes to stabilise water-in-water emulsions [66, 67].

510

511 **Conclusions and outlook**

512 The interactions between proteins and polysaccharides can be used to direct their association and,
513 ultimately, the characteristics of the resulting (emul)gels from a structural and
514 rheological/mechanical point of view. However, it is difficult to make comparisons between systems,
515 as different formulation and process parameters are involved and the intrinsic variability of natural
516 ingredients complicates the painting an overall picture. Much research has been done on an
517 increasing range of different systems at particular conditions driven by potential applications.
518 However, it remains a difficult task to predict behaviour of a particular mixtures at particular
519 conditions based on the behaviour of the individual components using general knowledge of the
520 interactions between proteins and polysaccharides. More systematic research on well-defined
521 systems with typical behaviours and covering a wide range of conditions may help to acquire more
522 general knowledge of the behaviour of (emul)gels formed by mixtures of these two types of
523 biopolymers. It is important to include the behaviour of the pure systems for comparison with that of
524 the mixtures. The type (associative or segregative) and extent (relative volume fractions) of phase
525 separation should be clearly identified. The choice of experimental conditions such as heating time
526 and duration should not be chosen arbitrarily, but should be motivated based on preliminary studies
527 in which they are varied. Nevertheless, it is clear that faced with new consumer demand for
528 healthier, environmentally-friendly foods, the use of in particular plant proteins in combination with
529 polysaccharides has excellent potential, eg in providing vegan alternatives for cheese and meat.

530

531

532

533 **References**

- 534 [1] Falsafi SR, Rostamabadi H, Samborska K, Mirarab S, Rashidinejhad A, Jafari SM. Protein-
535 polysaccharide interactions for the fabrication of bioactive-loaded nanocarriers: Chemical conjugates
536 and physical complexes. *Pharmacological Research*. 2022;178:1096-186.
- 537 [2] Cortez-Trejo MC, Gaytan-Martinez M, Reyes-Vega ML, Mendoza S. Protein-gum-based gels: Effect
538 of gum addition on microstructure, rheological properties, and water retention capacity. *Trends in*
539 *Food Science & Technology*. 2021;116:303-17.
- 540 [3] Yang X, Li AQ, Li D, Guo YR, Sun LJ. Applications of mixed polysaccharide-protein systems in
541 fabricating multi-structures of binary food gels-A review. *Trends in Food Science & Technology*.
542 2021;109:197-210.

543 [4] Liu K, Chen YY, Zha XQ, Li QM, Pan LH, Luo JP. Research progress on polysaccharide/protein
544 hydrogels: Preparation method, functional property and application as delivery systems for bioactive
545 ingredients. *Food Research International*. 2021;147:110542.

546 [5] Fan Z, Cheng P, Zhang P, Zhang G, Han J. Rheological insight of polysaccharide/protein based
547 hydrogels in recent food and biomedical fields: A review. *International Journal of Biological*
548 *Macromolecules*. 2022;222:1642-64.

549 [6] Hilal A, Florowska A, Wroniak MJG. Binary Hydrogels: Induction Methods and Recent Application
550 Progress as Food Matrices for Bioactive Compounds Delivery—A Bibliometric Review. *Gels*.
551 2023;9:68.

552 [7] Mezzenga R, Fischer P. The self-assembly, aggregation and phase transitions of food protein
553 systems in one, two and three dimensions. *Reports on Progress in Physics*. 2013;76:046601.

554 [8] Stephen AM, Phillips GO. *Food polysaccharides and their applications*: CRC press; 2016.

555 *[9] Zhang T, Yuan YX, Chai JL, Wu XL, Saini RK, Liu JB, et al. How does dextran sulfate promote the
556 egg white protein to form transparent hydrogel? the gelation mechanism and molecular force
557 changes. *Food Hydrocolloids*. 2022;133:107901. This study illustrates nicely the importance of
558 heating protocol and the necessity to combine SEM imaging with CLSM imaging in order to check the
559 influence of the several sample treatment required for the former

560 [10] Nath PC, Debnath S, Sridhar K, Inbaraj BS, Nayak PK, Sharma MJG. A Comprehensive Review of
561 Food Hydrogels: Principles, Formation Mechanisms, Microstructure, and Its Applications. *Gels*.
562 2022;9:1-25.

563 [11] Sarabi-Aghdam V, Hosseini-Parvar SH, Motamedzadegan A, Razi SM. Phase behavior and
564 rheological properties of basil seed gum/whey protein isolate mixed dispersions and gels. *Food*
565 *Science & Nutrition*. 2021;9:1881-95.

566 *[12] Hundschell CS, Bruhan J, Anzmann T, Kohlus R, Wagemans AM. Influence of Levan on the
567 Thermally Induced Gel Formation of beta-Lactoglobulin. *Gels*. 2022;8:228. This study demonstrates
568 the importance of both the molar mass of the polysaccharides and addition of salt on segregative
569 phase separation and its consequence for the mixed gel properties.

570 [13] He ZD, Ma TY, Zhang WW, Su EZ, Cao FL, Huang MG, et al. Heat-induced gel formation by whey
571 protein isolate- *Lycium barbarum* polysaccharides at varying pHs. *Food Hydrocolloids*.
572 2021;115:106607.

573 [14] Babaei J, Khodaiyan F, Mohammadian M, Sheikhi M. In vitro digestibility and functional
574 attributes of the whey protein heat-induced hydrogels reinforced by various polysaccharides and
575 CaCl₂. *Journal of Food Measurement and Characterization*. 2022;16:19-28.

576 [15] Jiang L, Zhang JH, Ren YM, Shen MY, Yu Q, Chen Y, et al. Acid/alkali shifting of *Mesona chinensis*
577 polysaccharide-whey protein isolate gels: Characterization and formation mechanism. *Food*
578 *Chemistry*. 2021;355:129650.

579 [16] Zhang JH, Jiang L, Yang J, Chen XX, Shen MY, Yu Q, et al. Effect of calcium chloride on heat-
580 induced *Mesona chinensis* polysaccharide-whey protein isolation gels: Gel properties and
581 interactions. *Lwt-Food Science and Technology*. 2022;155:112907.

582 [17] Guo N, Ma Y, Zhang F, Zhu G, Yu Z, Dai H, et al. Effect of pH on the thermal gel properties of
583 whey protein isolate-high acyl gellan gum. *Journal of the Science of Food and Agriculture*.
584 2023;103:3346-52.

585 [18] Johansson M, Johansson D, Strom A, Ryden J, Nilsson K, Karlsson J, et al. Effect of starch and
586 fibre on faba bean protein gel characteristics. *Food Hydrocolloids*. 2022;131:107741.

587 [19] Ran XL, Yang HS. Promoted strain-hardening and crystallinity of a soy protein-konjac
588 glucomannan complex gel by konjac glucomannan. *Food Hydrocolloids*. 2022;133:107959.

589 [20] Zhang D, Chen D, Patel B, Campanella OH. Pectin as a natural agent for reinforcement of pea
590 protein gel. *Carbohydrate Polymers*. 2022;298:120038.

591 [21] Jiang SS, Ma YY, Wang YH, Wang R, Zeng MY. Effect of k-carrageenan on the gelation properties
592 of oyster protein. *Food Chemistry*. 2022;382:132329.

593 *[22] Lu Z, Lee P-R, Yang HJFH. Kappa-carrageenan improves the gelation and structures of soy
594 protein isolate through the formation of hydrogen bonding and electrostatic interactions. *Food*

595 Hydrocolloids. 2023;140:108585. This article illustrates the complexity of gelation of
596 protein/polysaccharides mixtures where both components can gel depending on the temperature
597 and where pH dependent attractive and repulsive interactions play an important role.

598 [23] Piculell L. Gelling Carrageenans. In: Stephen AM, Philips GO, Williams PA, editors. Food
599 Polysaccharides and their Applications. 2nd ed. Boca Raton: CRC Press; 2006. p. 239.

600 [24] Lei YC, Zhao X, Li D, Wang LJ, Wang Y. Effects of kappa-Carrageenan and Guar Gum on the
601 Rheological Properties and Microstructure of Phycocyanin Gel. *Foods*. 2022;11:734.

602 [25] Liu JB, Chai JL, Yuan YX, Zhang T, Saini RK, Yang M, et al. Dextran sulfate facilitates egg white
603 protein to form transparent hydrogel at neutral pH: Structural, functional, and degradation
604 properties. *Food Hydrocolloids*. 2022;122:107094.

605 [26] Liu JB, Chai JL, Zhang T, Yuan YX, Saini RK, Xu ML, et al. Phase behavior, thermodynamic and
606 rheological properties of ovalbumin/ dextran sulfate: Effect of biopolymer ratio and salt
607 concentration. *Food Hydrocolloids*. 2021;118:106777.

608 [27] Zhuang XB, Wang LJ, Jiang XP, Chen YJ, Zhou GH. Insight into the mechanism of myofibrillar
609 protein gel influenced by konjac glucomannan: Moisture stability and phase separation behavior.
610 *Food Chemistry*. 2021;339:127941.

611 [28] Zhang T, Chen SJ, Xu XQ, Zhuang XB, Chen YJ, Xue Y, et al. Effects of konjac glucomannan on
612 physical properties and microstructure of fish myofibrillar protein gel: Phase behaviours involved.
613 *Food Hydrocolloids*. 2023;134:108034.

614 [29] Patole S, Cheng LR, Yang Z. Impact of incorporations of various polysaccharides on rheological
615 and microstructural characteristics of heat-induced quinoa protein isolate gels. *Food Biophysics*.
616 2022;17:314-23.

617 [30] Brito-Oliveira TC, Moraes ICF, Pinho SC, Campanella OH. Modeling creep/recovery behavior of
618 cold-set gels using different approaches. *Food Hydrocolloids*. 2022;123:107183.

619 [31] Bu KX, Huang DJ, Li DP, Zhu CH. Encapsulation and sustained release of curcumin by hawthorn
620 pectin and *Tenebrio Molitor* protein composite hydrogel. *International Journal of Biological*
621 *Macromolecules*. 2022;222:251-61.

622 [32] Ji ZL, Yu L, Duan QF, Miao S, Liu HS, Shen WY, et al. Morphology and Rheology of a Cool-Gel
623 (Protein) Blended with a Thermo-Gel (Hydroxypropyl Methylcellulose). *Foods*. 2022;11.

624 [33] You G, Niu GG, Zhou XY, Fan HL, Liu XL. Interactions involved in heat-induced gelatin gel
625 containing hsian-tsao gum, and mechanisms to improve its properties. *Journal of the Science of Food*
626 *and Agriculture*. 2023;103:820-8.

627 [34] Zhang XX, Liao BY, Guan ZJ, Thakur K, Khan MR, Busquets R, et al. Interaction between Gelatin
628 and Mulberry Leaf Polysaccharides in Miscible System: Physicochemical Characteristics and
629 Rheological Behavior. *Foods*. 2022;11:1571.

630 [35] Makarova AO, Derkach SR, Kadyrirov AI, Ziganshina SA, Kazantseva MA, Zueva OS, et al.
631 Supramolecular Structure and Mechanical Performance of kappa-Carrageenan-Gelatin Gel. *Polymers*.
632 2022;14:4347.

633 *[36] Li AQ, Guo C, Li XF, Li PY, Yang X, Guo YR. Gelation mechanism and physical properties of
634 glucono-delta-lactone induced alginate sodium/casein composite gels. *Food Hydrocolloids*.
635 2021;118:106775. In this and the related studies [37] and [38] the effect of different types of
636 polysaccharides (neutral and charged) on gelation of casein was investigated. The important effect of
637 the pH on the interaction was highlighted.

638 [37] Li XF, Guo C, Li PY, Sun JJ, Yang X, Guo YR. Structural characteristics of gluconic acid delta-lactone
639 induced casein gels as regulated by gellan gum incorporation. *Food Hydrocolloids*. 2021;120:106897.

640 [38] Li XF, Guo C, Yang X, Guo YR. Acid-induced mixed methylcellulose and casein gels: Structures,
641 physical properties and formation mechanism. *Food Chemistry*. 2022;366:130561.

642 *[39] Hu B, Hu J, Han LY, Cao JJ, Nishinari K, Yang JX, et al. Conformational transition and gelation of
643 kappa-carrageenan in electrostatic complexation with beta-lactoglobulin aggregates. *Food*
644 *Hydrocolloids*. 2021;118:106764. The potential influence of proteins on gelation of polysaccharides is
645 shown and the importance the aggregation state of the proteins is clearly demonstrated.

646 [40] Taheri A, Kashaninejad M. Rheological properties for determining the interaction of soluble cress
647 seed mucilage and beta-lactoglobulin nanocomplexes under sucrose and lactose treatments. *Food*
648 *Chemistry*. 2022;378:132133.

649 [41] Lin Q, Hu Y, Qiu C, Li X, Sang S, McClements DJ, et al. Peanut protein-polysaccharide hydrogels
650 based on semi-interpenetrating networks used for 3D/4D printing. *Food Hydrocolloids*.
651 2023;137:108332.

652 [42] Kazemi-Taskooh Z, Varidi M. Designation and characterization of cold-set whey protein-gellan
653 gum hydrogel for iron entrapment. *Food Hydrocolloids*. 2021;111:106205.

654 [43] Cortez-Trejo MC, Mendoza S, Loarca-Pina G, Figueroa-Cardenas JD. Physicochemical
655 characterization of protein isolates of amaranth and common bean and a study of their compatibility
656 with xanthan gum. *International Journal of Biological Macromolecules*. 2021;166:861-8.

657 *[44] Cortez-Trejo MC, Figueroa-Cardenas JD, Quintanar-Guerrero D, Baigts-Allende DK, Manriquez J,
658 Mendoza S. Effect of pH and protein-polysaccharide ratio on the intermolecular interactions between
659 amaranth proteins and xanthan gum to produce electrostatic hydrogels. *Food Hydrocolloids*.
660 2022;129:107648. This and closely related (43, 45) articles demonstrate the importance of the pH in
661 relation to the pI of the proteins for the properties of mixed protein/polysaccharide gels.

662 [45] Cortez-Trejo MC, Loarca-Pina G, Figueroa-Cardenas JD, Manriquez J, Mendoza S. Gel properties
663 of acid-induced gels obtained at room temperature and based on common bean proteins and
664 xanthan gum. *Food Hydrocolloids*. 2022;132:107873.

665 [46] He J, Peng ZL, Yang JX, Dai LX, Hua Z, Li LW. How does soy 7S globulin influence the thermo-
666 responsive fibrillation process of methylcellulose chains in aqueous solutions? *Colloids and Surfaces a-
667 Physicochemical and Engineering Aspects*. 2022;653:130064.

668 [47] Yan JN, Xue S, Du YN, Wang YQ, Xu SQ, Wu HT. Influence of pH and blend ratios on the complex
669 coacervation and synergistic enhancement in composite hydrogels from scallop (*patinopecten
670 yessoensis*) protein hydrolysates and Kappa-carrageenan/xanthan gum. *Lwt-Food Science and
671 Technology*. 2022;154:112745.

672 [48] Yao XL, Yao XX, Chen XY, Yue JX, Yang D, Liu N, et al. Construction of *Artemisia sphaerocephala*
673 *Krasch.* Polysaccharide based hydrogel complexed with pullulan and gelatin crosslinked by ferric ions.
674 *Food Chemistry*. 2022;373:131567.

675 [49] Cai ZX, Wei Y, Shi AM, Zhong J, Rao PF, Wang Q, et al. Correlation between interfacial layer
676 properties and physical stability of food emulsions: current trends, challenges, strategies, and further
677 perspectives. *Advances in Colloid and Interface Science*. 2023;313:102863.

678 [50] Grossmann L, McClements DJ. The science of plant-based foods: Approaches to create nutritious
679 and sustainable plant-based cheese analogs. *Trends in Food Science & Technology*. 2021;118:207-29.

680 [51] Ren YQ, Huang L, Zhang YX, Li H, Zhao D, Cao JN, et al. Application of Emulsion Gels as Fat
681 Substitutes in Meat Products. *Foods*. 2022;11:1950.

682 [52] Keramat M, Ehsandoost E, Golmakani M-T. Recent Trends in Improving the Oxidative Stability of
683 Oil-Based Food Products by Inhibiting Oxidation at the Interfacial Region. *Foods*. 2023;12:1191.

684 [53] Yalmanci D, Dertli E, Tekin-Cakmak ZH, Karasu S. The stabilisation of low-fat mayonnaise by
685 whey protein isolate-microbial exopolysaccharides (*Weissella confusa* W-16 strain) complex.
686 *International Journal of Food Science and Technology*. 2023;58:1307-16.

687 [54] Yao MX, Qi X, Zhang JH, Wang CY, Xie JH. Whey Protein Isolate-Mesona chinensis Polysaccharide
688 Conjugate: Characterization and Its Applications in O/W Emulsions. *Foods*. 2023;12:1068.

689 [55] Li M, Feng L, Xu YY, Nie MM, Li DJ, Zhou CS, et al. Rheological property, beta-carotene stability
690 and 3D printing characteristic of whey protein isolate emulsion gels by adding different
691 polysaccharides. *Food Chemistry*. 2023;414:135702.

692 [56] Shi F, Tian X, McClements DJ, Chang Y, Shen J, Xue C. Influence of molecular weight of an anionic
693 marine polysaccharide (sulfated fucan) on the stability and digestibility of multilayer emulsions:
694 Establishment of structure-function relationships. *Food Hydrocolloids*. 2021;113:106418.

695 [57] Juyang Z, Wolf B. Impact of Type of Sugar Beet Pectin–Sodium Caseinate Interaction on Emulsion
696 Properties at pH 4.5 and pH 7. *Foods*. 2021;10:631.

697 [58] Liu XY, Xue F, Adhikari B. Hemp protein isolate-polysaccharide complex coacervates and their
698 application as emulsifiers in oil-in-water emulsions. *Food Hydrocolloids*. 2023;137:108352.
699 [59] Liao W, Dumas E, Elaissari A, Gharsallaoui A. The formation mechanism of multilayer emulsions
700 studied by isothermal titration calorimetry and dynamic light scattering. *Food Hydrocolloids*.
701 2023;136:108275.
702 *[60] Lin DQ, Kelly AL, Miao S. The role of mixing sequence in structuring O/W emulsions and
703 emulsion gels produced by electrostatic protein-polysaccharide interactions between soy protein
704 isolate-coated droplets and alginate molecules. *Food Hydrocolloids*. 2021;113:106537. In this paper,
705 the authors point out the major effect of the addition order of the polysaccharide solution to the
706 protein phase on the structure of the resulting emulgels.
707
708 *[61] Li PY, Guo C, Li XF, Yuan K, Yang XD, Guo YR, et al. Preparation and structural characteristics of
709 composite alginate/casein emulsion gels: A microscopy and rheology study. *Food Hydrocolloids*.
710 2021;118:106792. The authors use a segregative phase separation to achieve emulgels with
711 interesting structural and mechanical properties.
712 [62] Sun C, Wang C, Xiong Z, Fang Y. Properties of binary complexes of whey protein fibril and gum
713 arabic and their functions of stabilizing emulsions and simulating mayonnaise. *Innovative Food
714 Science & Emerging Technologies*. 2021;68:102609.
715 [63] Dong Y, Wei ZH, Xue CH. Effect of interaction between ovotransferrin fibrils and pectin on
716 properties of oleogel-based Pickering emulsions. *Food Hydrocolloids*. 2023;140:108620.
717 [64] Su J, Guo Q, Yang S, Li H, Mao L, Gao Y, et al. Electrostatic deposition of polysaccharide onto soft
718 protein colloidal particles: Enhanced rigidity and potential application as Pickering emulsifiers. *Food
719 Hydrocolloids*. 2021;110:106147.
720 [65] Ge AL, Iqbal S, Chen XD. Alteration in rheology and microstructure of O/W emulsions using
721 controlled soy protein isolate-polysaccharide aggregation in aqueous phases. *Journal of Food
722 Engineering*. 2022;317:110872.
723 [66] Bahraseman NM, Shekarchizadeh H, Goli SAH. Segregative phase separation of gelatin and
724 tragacanth gum solution and Micking stabilization of their water-in-water emulsion with microgel
725 particles prepared by complex coacervation. *International Journal of Biological Macromolecules*.
726 2023;237:124250.
727 [67] Machado JPE, Capron I, de Freitas RA, Benyahia L, Nicolai T. Stabilization of amylopectin-pullulan
728 water in water emulsions by Interacting protein particles. *Food Hydrocolloids*. 2022;124:107320.
729